TITLE	DOCUMENT NUMBER REVISION	TOTAL PAGES
SPECIFICATION FOR ST-5 LI-ION BATTERY	ST5-495-006	24
	INITIAL	

71 111/33 2306 161 990

## **TECHNOLOGY DEVELOPMENT**

# NEW MILLENNIUM PROGRAM SPACE TECHNOLOGY 5 PROJECT

NANOSAT CONSTELLATION TRAILBLAZER PROJECT (CODE 495)

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION

GODDARD SPACE FLIGHT CENTER

GREENBELT, MARYLAND

ST5 CONFIGURATION CONTROL COPY
THIS DOCUMENT IS UNDER CONFIGURATION MANAGEMENT CONTROL. ANY CHANGES
REQUIRE ST5 PROJECT APPROVAL.

	AP	PROVALS	D.4.
Prepared By:	<u>Date</u>	Reviewed By:	<u>Date</u>
Original signed by: Karen D. Castell Project Technical Officer for Li-Ion Battery	07/21/00	Original signed by: Jaime Esper Project Systems Engineer	07/21/00
Reviewed By: Original signed by:	07/21/00	Reviewed By:  Original signed by: Robert B. Lilly	07/21/00
Eric J. Finnegan Project Technologist		Deputy Project Manager	
Reviewed By: Original signed by:	07/21/00	Approved By:	
Gopalakrishna Rao Staff Engineer		Thomas Yi Assistant Head, Space Power Applications Branch	
Reviewed By: Original signed by: Ronald E Perison	07/21/00		

Doc #: ST5-495-006

Revision: INITIAL

## **REVISION LOG**

Revision	Description	Date
		07/21/00

## TABLE OF CONTENTS

		٦.
1.0 <b>I</b> NTE	COPE	5
1.2	COPE DEFINITIONS	5
2.0 I	REQUIREMENTStem Definition	7
2.2 N		
2.2.1		
2.2.2		
2.≟.∠ 2.2. I		
2.3 I 2.3.1	ELECTRICAL INTERFACE	/
2.3.1 2.4 (		
2.4.1	Cell and Battery Performance Cell and Battery Design and Construction	y
2.4.2	Cell and Battery Design and Construction Cell and Battery Manufacturing	У
2.4.3		
2.5	Environment	. 11
2.6	REPORTINGREVIEWS AND DOCUMENTATION	. 11
2.7.1		
2.7.2		
2.8		
2.9.1	Product ChangesParts and Materials Traceability	14
2.9.2		
2.9.3		
2.9.4		
2.10	WORKMANSHIP  1 Fastener Certification	15
2.10.	1 Fastener Certification	15
2.10.	2 Fabrication Requirements	15
2.11	TESTING  1	16
2.11.	1 Pyroshock	17
2.11.	2 Random Vibration	17
2.11.	3 Sinusoidal Vibration	17
2.11.	.4 Thermal Vacuum Cycling and Thermal Cycling	18
2.11	.4 Thermal Vacuum Cycling and Thermal Cycling	18
2.11		
2.10	.6 Range Safety	18
2.12		
2.12		
2.12		
2.12		
2.12	.3 Cell Acceptance Testing	19
2.13		
2.13		
2.13		
2.13		
2.14		
2.14	HANDLING, STORAGE, PRESERVATION, MARKING, LABELING, FACKAGING & SIM THE	بے ر
2.15		
2.15		
2.17		
2.17	UNIT CHARACTERIZATION	2
1.10	I Market + and a second a second and a second a second and a second a	

Doc#:	ST5-495-006	Revision:	
2.19	VERIFICATION MATRIX		22
ADDES	INTY A. SIGNATURE CURVE ANALYSIS OF THE I	LITHIUM ION	CELLS23

Doc #: ST5-495-006

#### 1.0 INTRODUCTION

This Specification defines the general requirements for rechargeable Space Flight batteries intended for use in the ST-5 program. The battery chemistry chosen for this mission is lithium ion (Li-Ion).

#### 1.1 SCOPE

The contractor shall furnish personnel, service, parts, materials, equipment and facilities necessary to design, analyze, manufacture, inspect, test and deliver the space flight hardware in accordance with the requirements contained within this document.

#### 1.2 DEFINITIONS

Throughout this document, the term "C", or fraction of this term (e.g.C/2), will be used to describe the current for either charging or discharging the battery. The term "C" is a current numerically equal to the manufacturer's rated capacity in ampere-hours. Therefore, to charge a manufacturer's cell or battery rated at 20 ampere-hours at C/2 would be to charge the cell or battery at a current of 10 amperes.

Throughout this specification, TBS implies information required by the supplier whereas TBD or TBR implies information to be supplied or updated by the NASA/GSFC. All TBS/TBD requirements shall be negotiated during the preliminary and detailed designs and agreed to prior to the start of fabrication and assembly.

#### 1.3 ACRONYMS

Ah or Amp-hr	ampere-hour Acceptance Test Procedure Battery Buyoff Review current equal to manufacturer's rated capacity degrees Celsius Cell Buyoff Review charge/discharge Cell Critical Design Review depth of discharge Destructive Physical Analysis
EOC	end of charge
FMEA	Failure Mode Effects Analysis
GSFC	Goddard Space Flight Center
MCD	Manufacturing Control Document
MSR	Monthly Status Report
NASA	National Aeronautics and Space Administration
NDE	Non Destructive Evaluation
QA	Quality Assurance
Spec	Specification
ST-5	Space Technology 5
V/T	temperature-compensated voltage limit

## 1.4 APPLICABLE DOCUMENTS

#### 1.5 DRAWINGS

TBS Li-Ion Battery Interface Control Drawing
TBS Li-Ion Battery Electrical Schematic

Doc #: ST5-495-006

## 1.6 SPECIFICATIONS AND STANDARDS

The following documents provide information that is usually applicable to specific requirements for Space Flight batteries. However, in lieu of such specific requirements, the following documents may be used by the contractor as guidelines.

Qualification
Qualification
Quanneation
and Wiring
of PWB
Attributes
and Operation o
olled Environment
Society for Quality
latile Condensable
Environment
racking
or Fracture Contro
Assurance in Design
ng

## 2.0 REQUIREMENTS

#### 2.1 ITEM DEFINITION

The ST-5 Li-Ion Battery shall consist of two matched cells designed using Li-Ion chemistry and high tolerance separator technology to produce a stored energy capacity in a low volume, low weight package. The combination of chemical composition and high tolerance separator design shall achieve gravimetric and volumetric energy densities unachievable with current Li-Ion technology. The battery shall interface directly with the ST-5 Electrical Power Distribution Subsystem and shall provide sufficient telemetry to assess the health and safety of the battery during ground testing and on-orbit operations.

### 2.2 MECHANICAL INTERFACE

## 2.2.1 System Size, Volume and Mass

The center of mass and dimension for the battery shall be identified on the Battery Interface Control Drawing. The mass, size and volume requirements shall be as specified in Table 2.

## 2.2.2 Structure Mounting

The location of mounting hardware for the battery shall be specified on the Battery Interface Control Drawing. The physical mounting technique, including surface, thermal and electrical requirements shall be as specified in Table 2.

## 2.2.3 Harness Connections

The contractor shall be responsible for all necessary Battery internal harnessing. The location and orientation of all connectors in addition to the routing of all internal harnessing shall be identified on the Battery Interface Control Drawing. The system internal and external harnessing and connection requirements shall be as specified in Table 2, including connector type and wire type requirements.

### 2.3 ELECTRICAL INTERFACE

The Battery shall interface directly with the ST-5 Electrical Power and Distribution Subsystem (EPS).

## 2.3.1 Telemetry and Command

All telemetry from the battery shall be facilitated as an interface with the ST-5 EPS subsystem. The EPS subsystem shall then be responsible for interfacing with the ST-5 C&DH subsystem for transmission of information to the ground.

#### 2.4 CHARACTERISTICS

The battery shall meet all requirements of this specification over the design life and with the environments defined in section 2.5. Beginning of life (BOL) test limits shall be de-rated as necessary to meet the end of life (EOL) requirements defined below.

#### Doc#: ST5-495-006

## 2.4.1 Cell and Battery Performance

The contractor shall design the cell and battery to meet the requirements in this document. The contractor shall prepare and submit cell and battery design and performance specifications including mechanical drawings in accordance with the Mission Unique Requirements given in Table 3, the Battery Performance Requirements specified in Table 1 and the Battery Design Requirements specified in Table 2. The contractor shall perform analyses to demonstrate that the cells will meet the performance and life requirements specified in this document. Battery analyses shall be submitted as a part of the Cell Critical Design Package. GSFC shall perform the thermal and structural analyses. The contractor shall provide inputs to these models and shall perform tests at different battery charge and discharge rates to validate these models.

## Table 1: Cell & Battery Performance Requirements

Table 1: Cell & Battery Performance Requireme	ents
Battery Voltage from 0% to 100% of Rated Capacity (Volts):	6.0 to 8.1 (3.0-4.05 per Cell)
Battery Nameplate Capacity @ 25 deg C at C/2 rate, at end of life	> 5 Ah 0.80 * C
Battery Capacity at C/2 rate:@ -10 degrees C	1.00 C
@ 40 degrees C	1.05 * C 1
Cell Capacity and Cell Impedance Matching between cells within a battery y (at -10	1370
Battery Canacity and Impedance Matching between batteries from the same cell lot	± 3 70
Charge Retention after 72 hours of open circuit @ 25 degrees C	<=8% per month
Maximum Battery Internal Impedance	100 Mohms at 100 V dc
Maximum End of Charge Voltage	8.1 Volts (4.05 Volts per cell)
Minimum End of Discharge Voltage at required capacity	(3.0 Volts per com)
Charge Control methods for battery operation	Correspondent and a second
Maximum Battery Charge Rate  Voltage after Peak Load (C/2 for 1 hr +2*C for 5 mins at 25 deg C)	. 6.0 Volts
Flight Operating Temperature Range:Ascent:	(3.0 Volts per cerr)
Flight	, -10 deg e to 40 deg e
Flight Operating Life	. 103
Shelf Life (vendor shall advise when to activate flight cells in order to span mission life)	years (400 cycles, 0070 Boz,
Operating Environmental Pressure Range	" 1 atmosphere to 10 <sup>-6</sup> torr
Sealed cell/battery proof pressure	1.5 times max operating pressure 3.0 times operating pressure (leak before burst)
Minimum Resonance Frequency	100 Hz 1.4 times flight loads
Ultimate strength	

## 2.4.2 Cell and Battery Design and Construction

The Battery shall be designed in accordance with the stipulations presented in Table 2 and the following guidelines.

- (a) ESD mitigation...... Internal metallic items (part spot shields, heat sinks, etc) shall have < 1 Gohm (TBR) dc resistance to ground (i.e., no floating metal).

## Table 2: Cell & Battery Design

	able 2: Cell & Battery Design
Pattery Type	Contractor shall provide Lithium Ion cells that meet the requirements of this
Battery Rated Capacity	Contractor shall specify the ampere-hour size (C) of each battery based at 25 degrees C to meet the depth of discharge & number of charge/discharge cycles for this mission; also, contractor shall provide this data as well as capacity data at the temperature extremes of the mission.
	Contractor shall specify the battery mass including mass breakdown of cells to their battery components. Maximum battery mass shall not exceed 382g.
	Contractor shall specify the battery dimensions in all directions including a description of where clearances and access are required to accommodate electrical and mechanical integration to the battery. Battery volume shall not exceed 6.67x6.35x6.35 cm.
	Contractor shall specify the battery mounting surface including the Interface material finish, area, pattern, smoothness, and mounting holes.
Battery Structural	Contractor shall specify the battery structural design that meets all integrity design qualification levels for the launch environments as specified in section 2.11; also, contractor shall provide inputs to the GSFC structural analysis and shall perform tests to validate the GSFC model.
Battery Thermal	. Contractor shall provide GSFC with inputs for the GSFC-generated thermal model. The contractor shall perform testing at various charge/discharge rates to validate this model.
Battery Electrical Power Interface	Contractor shall provide the electrical interface for flight power and shall indicate the type, quantity, & size of wiring, connectors, and grounding. The battery shall have suitable interfaces (connectors) for power, battery telemetry and for ground support. Contractor shall provide the electrical interfaces for individual cell monitoring. All monitoring circuits will be located on the spacecraft side and will be the responsibility of GSFC.
Battery Materials	Contractor shall provide a list of all battery materials and shall identify outgassing levels and resistance to moisture/corrosion damage during ground operations, if known.
Battery Telemetry	Contractor shall install one temperature sensor per cell prior to battery assembly. The location of sensors shall be indicated on the Battery Interface Control Drawing.
	ified by the contractor an submitted to GSFC for approval
The items in this table shall be spec-	iffed by the contractor an submitted to Got o 101 approximately

## 2.4.3 Cell and Battery Manufacturing

The Contractor shall provide all the necessary manufacturing resources to fabricate flight quality cells and batteries in accordance with this document. The contractor shall manufacture and deliver all hardware identified herein and listed in the contract schedule.

Doc #: ST5-495-006 Revision: Initial

## 2.4.3.1 Cell Fabrication

Cell fabrication shall meet the requirements of this document and shall be in accordance with the contractor-generated GSFC-reviewed and mutually agreed upon Cell Manufacturing Control Document. The Cell Manufacturing Control Document shall include a detailed plan for the cell fabrication and assembly flow, parts list, materials list, test procedures and customer inspection points.

## 2.4.3.2 Battery Fabrication

Battery fabrication shall meet the requirements of this document and shall be in accordance with the contractor-generated GSFC-reviewed and mutually agreed upon Battery Manufacturing Control Document. The Battery Manufacturing Control Document shall include a detailed plan for the battery fabrication, assembly flow, parts list, materials list, test procedures and inspection points.

#### 2.5 ENVIRONMENT

The Battery shall be designed to operate properly in accordance with the stipulations presented in Table 1, Table 3 and the following environmental requirements.

- (a) Radiation..... (See Table 3)
- (b) Thermal
  - (i) Operating (deg C):.... (See Table 1)
  - (ii) Transients:.....xx °C swing over a xx min duration (TBD)
  - (iii) Life Cycles:..... (See Table 3)
    - (a) Launch Loads (g's):
- 11; Each Axis
- (b) Pyroshock (in/sec):TBD
- (c) Transport Loads (g's): TBD

## Table 3: Mission Unique Requirements

Orbit		200 km by 6.6*Re Altitude
		10.52 Hrs Period (in-sun=8.64 hr; eclipse=1.88 hr)
Solar Orientation to vehicle	spin axis	90 degrees +/- 25 degrees
Mission Life		> 3 months
Datter Operating Tempera	iture:	-10 degrees C to 40 degrees C
Charge/Discharge Cycles	Flight:	400 cycles at depth of discharge 60% of shallower
Charge Diocharge 1)	Ground:	100 cycles at depth of discharge 100%
Discharge Load		
Discharge Duration	Pre-Launch	TBD Hours
D1001101 60 2 11 11 11 11 11 11 11 11 11 11 11 11 1	Ascent:	TBD Hours
	Flight:	1.88 Hours maximum per orbit
Charge Duration		8.64 Hours or greater per cycle
Depth of Discharge Limit	During Mission	60% (or shallower if required to meet all performance requirements during the entire mission)
Radiation ToleranceTotal Ionizing Dose (TID): Linear Energy Transfer (LET):		100krad
		TBD MeV-cm^2/mg

#### REPORTING 2.6

The contractor shall participate in status telephone conferences (telecons) as required to communicate progress and problems. This is an informal exchange of information and status. The content shall include a summary of the period's schedule progress, issues, problem areas, and activities on-going Other subject matter covered may include definition of technical interfaces and component characteristics. The contractor and GSFC Technical Officer (TO) may mutually decide that some combination of telecons and e-mail communication on a different time interval is a more efficient way to pass information and status. At a minimum, status shall be communicated to the TO monthly. Note that the GSFC Technical Officer (TO) may also be referred to as the Contracting Officer's Technical Representative (COTR). The GSFC Technical Officer and/or her/his designee shall have access to all unrestricted areas and facilities where work is being performed on this contract. Escorted access to the contractor's restricted work areas related to this contract shall be provided to GSFC. The contractor's point of contact shall be notified prior to escorted access into restricted areas.

## 2.7 REVIEWS AND DOCUMENTATION

#### Reviews/Meetings 2.7.1

The contractor shall conduct all reviews at his facility and provide schedule status and the noted data and responses. Reviews shall be on or before the dates established between the GSFC Technical Officer and the contractor's point of contact. A Review shall not be considered closed until all open action items have been completed.

#### Cell Critical Design Review 2.7.1.1

A Cell Critical Design Review (CCDR) shall be conducted following cell and battery design, but prior to fabrication. The review shall provide GSFC with cell and battery design data and analysis to show an overall compliance with the battery requirements.

#### Cell Buy-off Review 2.7.1.2

A Cell Buy-off Review (CBR) shall be conducted following cell fabrication and acceptance testing, but prior to start of battery build. Cell acceptance data and all other data contained within the Cell Test Data Package shall be presented to demonstrate to GSFC the adequacy of each cell lot.

#### Battery Buy-Off Review 2.7.1.3

A Battery Buy-off Review (BBR) shall be conducted prior to battery delivery. Battery acceptance data and all other data contained within the Battery Data Book shall be presented to GSFC to demonstrate compliance with all requirements.

#### **Documentation** 2.7.2

The contractor shall generate and maintain all documentation required to manage the work effort, document the design and verify that the design and hardware are in accordance with contractual requirements. The Contractor shall maintain color photographs to document the work under this The Contractor shall choose what to document, and this shall include physical cell characteristics, test setups, anomalies, repairs, and hardware status throughout the cell and battery assemblies and test phases. The contractor shall make these photographs available to GSFC upon request.

## 2.7.2.1 Cell Critical Design Data Package

The manufacturer shall provide to GSFC a cell critical design data package. The data package shall be delivered 15 days prior to the date of the review. This data package shall provide all cell and battery design and analysis which ensures the proposed design meets all the requirements in this document and is in sufficient detail for fabrication to begin. At a minimum, the design package shall include the following:

Drawing package including: parts list, and design, assembly and interface drawings, process flow/travelers, customer inspection points

Materials and Process List,

Electrical interfaces,

Battery Handling and Storage Plan,

Qualification and Acceptance Test Plan/Procedure.

The following data items shall be furnished by GSFC, in coordination with the contractor, and included as part of the data package:

Failure Modes Effects Analysis,

Thermal analysis,

Mechanical/Structural analysis.

## 2.7.2.2 Cell Test Data Package

Fifteen days prior to the Cell Buyoff Review, the contractor shall make available to GSFC a Cell Test Data Package. The data package shall contain cell fabrication and test data. (The Contractor is not required to furnish propriety information in hard copy form, but shall provide cell data (which may be transformed into relative characteristics) for review and concurrence at the plant by a GSFC battery engineer.) The package shall also include Signature Curve Analysis of the cells if the Contractor has performed this optional test (Refer to Appendix A for test description).

## 2.7.2.3 Meeting/Review Data Package

Following completion of a scheduled review/meeting as specified by section 2.7.1, the contractor shall produce a meeting/review data package for review and concurrence by GSFC. The data package shall include the following minimum information:

Meeting Minutes as provided by contractor.

Review Presentation material, to include all errata.

Attendance List.

Action Items, including closure date and responsibilities.

Any verbal or written agreements.

## 2.7.2.4 Cell and Battery Manufacturing Control Document

A Manufacturing Control Document (MCD) shall be prepared upon completion of the cell and battery design. The MCD shall include all applicable specifications, drawings, flowcharts, inspection points, test specifications, and any other documentation to which the cells and batteries are built and tested. The contractor shall provide these documents to GSFC for review and concurrence. The MCD provided to GSFC may have proprietary information excluded, but must include a list of the proprietary information with all document numbers and revision numbers

#### Battery Data Book 2.7.2.5

A Battery Data Book shall be provided for each battery. The data book shall include all battery fabrication and test data and any other information necessary to ensure the battery meets the requirements of this document. The battery data book shall be presented to GSFC at the BBR. The data book shall include, as a minimum, the following:

As-built configuration list.

Open items list and reason for being open.

As run test procedures with test results.

Closed failure reports.

A summary of all deviations and waivers applicable to deliverable items.

Critical parameters trend data.

Logbook including total operating time and cycle records.

Battery fabrication and qualification/acceptance test data.

Plate test data (if applicable) and cell fabrication and test data.

Evidence of acceptance by contractor QA.

#### Cell and Battery Qualification and Acceptance Test Plan/Procedure 2.7.2.6

The manufacture shall produce a Qualification (QTP) and an Acceptance Test Plan/Procedure (ATP). The QTP and ATP shall be made available to the government for review and acceptance as part of the CCDR. The ATP shall be a subset of the QTP tests. QTP tests shall be conducted on a dedicated test article (Qualification unit) which is flight representative. ATP tests shall be conducted on all flight units.

#### Battery Shipping Handling and Storage Plan 2.7.2.7

The manufacturer shall prepare and provide for GSFC use a Battery Shipping Handling and Storage Plan. This plan shall provide the manufacturer's recommended procedures for all aspects of cell and battery handling to prevent performance degradation before flight. The plan shall include but not be limited to the following information:

Transportation and storage handling, including charge state, battery configuration and temperature.

Pre-launch and post-storage reconditioning procedures, including charge/discharge and rates and a timeline of events.

Temperature, Discharge and charge rate limits.

Undervoltage and overvoltage limits.

## 2.8 QUALITY ASSURANCE PROVISIONS

The Contractor shall implement a Quality Management System that complies with the spirit of ANSI/ASQC 9001-1994 and supply GSFC with their Quality Assurance Manual for review and concurrence. Third party certification/registration is not required. This system shall apply to all flight hardware, flight spares and critical GSE. It is recognized that some contractors currently maintain a Quality System that is not compliant with ISO 9001 Quality Requirements, but complies with the essence of ISO 9001. Because of the similarity of these quality systems, the contractor may request a deviation to meeting the full requirements of ANSI/ASQC9001-1994 for this contract only. Approval of the deviation shall be contingent on the contractor listing which of the 20 ISO elements (ANSI/ASQC 9001-1994 paras. 4.1 to 4.20) they are not compliant with along with a justification or plan for becoming compliant. GSFC shall be notified of any changes to the status of the QA program.

## 2.9 PARTS, MATERIALS AND PROCESSES

## 2.9.1 Product Changes

The GSFC shall be notified when the Contractor or the Contractor's suppliers propose changes to products, including: (a) changes in design, parts, materials, fabrication methods or processes, and (b) changes which may affect the quality or intended end use of the item. Any proposed changes shall require GSFC concurrence.

## 2.9.2 Parts and Materials Traceability

The contractor shall maintain traceability of parts and materials for the purpose of maintaining unique identification of the product throughout the procurement Receiving Inspection and Test System that is in compliance with 4.10.2 through 4.10.2.2 of ANSI/ASQC9001-1994.

#### 2.9.3 Parts

All part, materials and processes shall be selected and screened. Parts, materials, contractor's screening process and processes lists shall be submitted to the government for review and concurrence as part of the MCD.

Electronic parts shall require radiation lot acceptance testing (RLAT) unless the radiation design margin (RDM) against the calculated exposure based on part test data (from 3 vendor date codes) is greater than five or the RDM based on generic test data exceeds 10. Radiation exposure levels shall be calculated with a ray trace method. Parts as shielded in the unit enclosure shall meet the predicted environment or equivalently parts should be shielded to one half the dose that the circuit can tolerate. All analyses shall be documented in and available for review and concurrence by the government and shall use appropriate part radiation de-ratings, shielding analysis and methodology.

#### 2.9.4 Materials

In general materials shall be selected with a TML (Total Mass Loss) of < 1.0% and a CVCM (collected volatile condensable material) < 0.1%... Proposed materials and processes shall be reviewed and mutually agreed upon with the GSFC Materials Consultant. A list of these materials shall be provided to GSFC within 1 month of contract award. The developer shall maintain lists of these items (inorganics, metallics, polymerics, lubricants, and processes) and appropriate usage records.

Disclosure of proprietary materials and processes are not required. However, proprietary materials and processes shall be available for review and concurrence at contractor's and subcontractor's site. All noncompliant materials shall require the submission of a Materials Usage Agreement (MUA) to the GSFC for approval.

Doc #: ST5-495-006

#### 2.10 WORKMANSHIP

All parts and assemblies shall be designed, constructed and finished in a quality manner intended to produce defect free equipment. Particular attention shall be given to critical operations such as handling of items sensitive to ESD, cleanliness and contamination controls, electronic soldering and assembly, connector crimping and harness assembly, test and inspection and other pertinent manufacturing controls. The unit shall be free of sharp edges or corners which may cut or abrade thermal blankets. Workmanship shall be per MIL-STD-454 (TBD).

## 2.10.1 Fastener Certification

The Contractor shall comply with S-313-100, Goddard Space Flight Center Fastener Integrity Requirements for structural fasteners. Traceability shall be maintained for every fastener lot.

## 2.10.2 Fabrication Requirements

The following commercial or NASA workmanship standards may be used as guidelines for the work under this contract. Best commercial practices or equivalent standards used by the contractor are acceptable and may be review and concurrenceed by GSFC Quality Assurance:

NHB5300.4 (3A-2)
NHB 5300.4(3G)
NHB5300.4(3H)
NHB 5300.4(3J)
IPC-D-2/3
[NASA alternative-NHB 5300.4 (3K)]
EIA-623
[NASA alternative-NHB 5300.4 (3L)]

The developer shall provide printed wiring board coupons to GSFC, or to a GSFC approved laboratory for evaluation (TBD). Approval shall be obtained prior to population of printed wiring boards (TBD).

#### 2.11 TESTING

The testing program for the Battery shall be designed according to the following requirements:

- (a) Initial (pre-environment) and Final (post-environment) Performance Tests (to include mission specific cycling, temperature range, rates, DOD, etc.) shall be conducted to establish data for trending comparison. Unexpected non-repeatability across environments shall be treated as a failure. Performance testing to the extent practicable shall also be conducted during thermal cycling to verify critical performance compliance over the Acceptance temperature range. During all environments the unit shall be powered and perceptive parameters shall be continuously monitored for failures or intermittent operation. General test guidelines shall be per MIL-STD 1540C and/or MIL-STD-810 (TBD). Note that Qualification Testing shall be preformed on the Protoflight or Qualification unit while Acceptance Testing shall be done on the Flight Units.
- (b) Connector savers shall be used for all testing to minimize mate/de-mate of the flight connector.
- (c) Test Tolerances are as follows:

Table 4: Environmental Test Tolerances

Condition	Tolerance
Temperature	±3 °C
Pressure Above 1 Torr 0.01 Torr to 1 Torr Below 0.001 Torr Relative Humidity Acoustic Vibration - Sound Pressure Levels 1/3-Octave Band Overall SPL	±10% ±25% ±80% ±5% ±3.0 dB ±1.5 dB
Vibration Frequency (Hz)	±2%
Random Vibration Acceleration  Power Spectral Density (G²/Hz) 20 to 500 Hz (25 Hz or narrower) 500 to 2000 Hz (50 Hz or narrower)  Random overall GRMS  Shock Response (Q=10) 1/6 Octave band center frequency amplitude (G's)	±1.5 dB ±3.0 dB ±1.5 dB
0-2000 Hz	±6 dB with 30% of the response spectrum center frequency amplitude greater than nominal test specifications + 10 dB/-6dB
>2000Hz	±5%
Static Load	+/- 10%
Acceleration (static) Sinusoidal Vibration Amplitude Test Duration	+/- 10% 10%

## (d) Test Levels are as follows:

Table 5: Environmental Test Levels

	Acceptance (Flight Units)	Protoflight (Qualification Unit)				
Pyroshock	Not Required	MPE +3 dB 2 shocks/axis;3 axes				
Random Vibration	MPE Flight Duration#/axis; 3 axes	MPE Flight Duration#/axis; 3 axes				
Sinusoidal Vibration	Not Required	MPE Flight Duration*/axis; 3 axes				
Structural Loads	Not Required	1.25 x flight loads				
Thermal-Vacuum Cycle	MPE ± 10 °C; 8 cycles	MPE ± 10 °C; 4 cycles 1 x 10 <sup>-4</sup> Torr				
Pressure	Proof test (1.5 x MEOP) Leakage Test (MEOP)	Proof test (1.5 x MEOP) Leakage Test (MEOP)				
Burn-In	200 hrs total failure free on-time	200 hrs total failure free on-time				
EMI/EMC/Magnetics	As Specified	As Specified				

(MPE) Mission Predicted Environment see section 3.5

- (\*) Test not required for protoflight if addressed by random vibration levels
- (#) Flight duration or minimum of one minute

## 2.11.1 Pyroshock

- (a) Qualification unit shall be tested per the maxi-max Shock response spectra (Q=10).
- (b) Two shock exposures in each of 3 axes shall be applied.

#### Doc #: ST5-495-006

#### Random Vibration 2.11.2

- (a) Random vibration levels are Gaussian with peak G's limited to 30 with tolerances.
- (b) Unit shall be un-powered during the test.
- (c) Qualification unit shall be instrumented to verify the unit's fundamental frequencies (first modes
- (d) The following test profile shall be used for both the qualification and flight units as appropriate.

ASD Level (G<sup>2</sup>/Hz) Frequency Protoflight Acceptance (Hz) (Flight) (Qualification) 0.013 0.026 20 +6 dB/Oct +6 dB/Oct 20-50 0.08 0.16 50-800 -6 dB/Oct -6dB/Oct 800-2000 0.013 0.026 2000 10.0 Grms

14.1 Grms

Table 6: Random Vibration Test Profile

#### Sinusoidal Vibration 2.11.3

(a) Sinusoidal Vibration shall only be necessary if both FEM analysis and Random vibration testing show response at frequencies below 60 Hz.

#### Thermal Vacuum Cycling and Thermal Cycling 2.11.4

Overall

- (a) Perceptive parameters shall be monitored continuously throughout the test during all temperature and pressure transitions. Critical performance or functional tests shall be conducted at the temp extremes (after sufficient soak time to ensure internal equilibrium) and at the initial and final ambient temps while varying pertinent interface parameters (bus voltage, command logic levels, etc) and while operating in all possible modes. Critical temps should be monitored throughout the test and alarmed if possible.
- (b) The unit shall be mounted in a flight like manner for Thermal-Vacuum testing.
- (c) Unit average baseplate temperature shall be used as the temperature reference for all tests.
- (d) Unit (powered or unpowered ) shall not fail or suffer permanent degradation at the survival temp limits. Each unit shall undergo a minimum of one cycle to survival temp limits (minimum dwell time of 1 hr).
- (e) Unit shall be capable of turn on as well as meet full performance over the qualification temperature range. Each unit shall undergo a minimum of two hot and cold turn on demonstrations at the applicable temperature extremes.
- (f) Average temperature transition rate shall be > 1°C/minute, each transition.
- (g) A four hour dwell (minimum) after temp stabilization to <3C/hr at each temperature extreme shall be established for each cycle.
- (h) Performance and functional tests shall be exercised at temperature extremes of the first and last cycles. Mission specific information for the battery testing (rates, temperature extremes, DOD, cycles, etc) are contained in Tables 1 and 3.

#### Doc#: ST5-495-006

(i) At the survival limits, the unit shall be turned off, then cold started after a soak period sufficient to ensure unit internal temperature has stabilized then the unit shall be turn off, then hot start after electrical components have discharged.

#### 2.11.5 Pressure

(a) Nominal vacuum pressure for testing is 1x10 <sup>-5</sup> Torr.

### 2.11.6 Range Safety

(a) The battery design must meet the requirements of the range safety document, EWR 127-1. Safety testing shall be done by the contractor at the contractor's facility.

## 2.10.7 EMI/EMC/Magnetics

**TBD** 

### 2.12 QUALIFICATION

### 2.12.1 Cell Qualification

Cell qualification shall meet the requirements of this document. Cell qualification by similarity with a previously flight-qualified cell of the same capacity and design is acceptable. However, the contractor must provide proof through cell life test and flight experience that an existing cell design of the same capacity, which has been fabricated under an existing MCD and has been flight qualified to specifications which envelope the requirements specified within this document. In the absence of previous qualification data, cell qualification testing shall be required and the appropriate testing program provided in the Qualification and Acceptance Test Plan/Procedure.

## 2.12.2 Battery Qualification

Battery qualification shall meet the requirements of this document. Battery qualification by similarity with a previously flight-qualified cell is acceptable. However, the contractor must provide proof through cell life test and flight experience that an existing cell design, which has been fabricated under an existing MCD has been flight qualified to specifications which envelope the requirements specified within this document. In the absence of previous qualification data, battery qualification testing shall be required and the appropriate testing program provided in the Qualification and Acceptance Test Plan/Procedure.

## 2.12.3 Cell Acceptance Testing

Cell acceptance testing shall meet the requirements of this document and shall be detailed in the Qualification and Acceptance Test Plan/Procedure.

## 2.12.4 Battery Acceptance Testing

The contractor shall perform the testing required by this document and shall be documented in the Qualification and Acceptance Test Plan/Procedure. Testing shall be performed to verify that all the requirements are met. The minimum required battery acceptance testing shall be as specified in Table 7. The battery shall continue to meet performance and mission requirements during and after exposure to the launch and operational environments specified in this document. The contractor shall provide all data measurements taken at convenient intervals during the battery acceptance tests.

Doc #: ST5-495-006

Revision: INITIAL

## Table 7: Battery Acceptance Test Procedure

### Physical Measurements

The contractor shall measure the mass of the battery to the nearest gram and the center of mass of the battery to within a tolerance of  $\pm 0.25$  cm.

#### Visual Inspection

The contractor shall visually inspect the battery to verify that the battery complies with all design specifications and has no visual deffects.

#### **Functional Testing**

CHOURT 1 caring	
Flectrolyte Leak Check:	No cell or battery shall exhibit electrolyte leakage
Indian Pagistance Check:	100 Mohms or greater at 100 V DC
Isolation Resistance Checkenster	Maintain calibration & specifications over
Temperature Sensor Checkout	temperature range
Room Temperature Capacity Test:	1.0*C or greater (@ 25 deg C)
Charge Detention Test:	0.98*C or greater after open circuit for 72 hours
	((a) 25 deg C)
Peak Load Test	6.0 V or greater after C/2 discharge for 1 hour plus
Tour Boad Testimina	2*C discharge for 5 minutes

## Launch Environment (Battery on Discharge)

Static Load (may not be required for follow-on units)

Random Vibration

Sine Vibration

#### Visual Inspection

#### **Functional Testing**

## Flight Thermal Vacuum Environment

Soak at +50 degrees C and at -45 degrees C for the Qual battery, -15 deg C for the Flight batteries for a minimum of 4 hours

Electrical Performance/Mission Profile Cycles at + 25 degrees C: Contractor-specified/GSFC-approved

Electrical Performance/Mission Profile Cycles at -10 degrees C: Contractor-specified/GSFC-approved

Electrical Performance/Mission Profile Cycles at +40 degrees C: Contractor-specified/GSFC-approved

## Capacity Measurements (in the following sequence)

Canacity Test	@25 degrees C:	1.00*C or greater
-	@-10 degrees C:	0.80*C or greater
	@40 degrees C:	1.05*C or greater
	@25 degrees C:	1.00*C or greater

#### Visual Inspection

Functional Testing (GSFC will provide mission specific information for testing: rates, DOD, temperature range, cycles, as described in Tables 1 and 3).

## 2.13 CONTROL, REPORTING AND DISPOSITION

### 2.13.1 Contamination Control

The quality assurance personnel shall ensure that the requirements for cleanliness and contamination control are being complied with during all phases of the program.

## 2.13.2 Non-Conformance Control

The Contractor shall operate a closed-loop nonconformance control system for failures and discrepancies compliant with ANSI/ASQCQ9001-1994. The Contractor shall identify each nonconformance in a Material Review Board (MRB) as minor or major. A major nonconformance is defined as affecting reliability, workmanship, performance, safety, interfaces, or other approved GSFC documentation. Minor non-conformances are superficial or cosmetic flaws. All major nonconformances shall be submitted to the GSFC Quality Assurance Representative for approval MRB's involving minor non-conformances may be dispositioned and approved by the contractor. Minor MRB's shall be documented and provided to the GSFC Technical Officer within 48 hours of disposition.

## 2.13.3 Failure Reporting

A failure report shall be immediately written for any departure from design, performance, testing, or handling requirements that affect the function of the flight segment or flight support equipment or could possibly compromise mission objectives. The Technical Officer shall be notified verbally and/or by email within 24 hours of the malfunction. Written notification in the form of a GSFC Problem/Failure Report (P/FR) or contractor equivalent form shall be made within 48 hours. Routine submission of formal P/FR shall begin with the start of performance testing of the component at the box level and it shall continue through formal acceptance by the GSFC project office.

Other problems or anomalies that are unusual or that might affect other areas of the spacecraft shall also be cited on a P/FR. Failures that occur prior to box-level acceptance testing shall be reported at the next status review. GSFC retains the option to require that a formal P/FR be submitted on a case by case basis for any failures reported at this level.

#### HANDLING, STORAGE, PRESERVATION, MARKING, LABELING, PACKAGING & SHIPPING 2.14

Products shall be stored, preserved, marked, labeled, packaged, and packed to prevent loss of marking, deterioration, contamination, or damage during all phases of the program. Stored and stocked items shall be controlled in accordance with documented procedures and be subject to quality surveillance.

## 2.14.1 Handling and Shipping

The contractor shall be responsible for the protection of the deliverable items during handling, transporting and delivery. The contractor shall provide all materials and personnel required to design, fabricate, and test the necessary handling fixtures, shipping containers, packaging material, and labeling to protect the completed cells and batteries against contamination, excessive condensation and moisture, and damage during handling, transportation, and delivery. The shipping containers shall include shock, temperature, and humidity recorders and shall be capable of accommodating cold packs for prolonged shipping conditions, if necessary. GSFC will work with the contractor to devise a mutually agreeable plan for selecting and mounting the shock recorders. A reliable method will be devised to monitor shock, while reducing the potential for false readings. These indicators may be furnished to the contractor by GSFC. The contractor shall be responsible for obtaining all documents and approvals for shipping batteries to the GSFC in accordance with this document.

Prior to shipping, quality assurance personnel shall ensure that:

- (a) Fabrication, inspection, and test operations have been completed and accepted.
- (b) All products are identified and marked in accordance with requirements. Shipping containers carrying flight hardware are clearly labeled as such.
- (c) The accompanying documentation (contractor's shipping and property accountable form) has been reviewed for completeness, identification, and quality approvals.

Doc#: ST5-495-006

- (d) Packaging and marking of products, as a minimum, comply with Interstate Commerce Commission rules and regulations and are adequate to ensure safe arrival and ready identification at their destinations.
- (e) The loading and transporting methods are in compliance with those designated in the shipping documents.
- (f) Integrity seals are on shipping containers.
- (g) Special handling instructions for receiving activities are provided where appropriate, including proper labeling of containers and related documents to provide evidence of this verification. The contractor may use "best commercial practices" for packaging and shipping and has responsibility for any damage incurred during shipment.

#### GOVERNMENT ACCEPTANCE 2.15

Prior to acceptance by GSFC, quality assurance personnel shall ensure that deliverable end-items, including the Battery Data Book containing the verification data, are in accordance with development plan or contract requirements. A copy of the data package shall be submitted to GSFC in accordance with the contract and a copy shall accompany each end-item.

Final acceptance of the units shall be performed by the GSFC technical representative at GSFC and shall be based on an inspection of each unit for any shipping damage. The units will be conditionally accepted at the contractor's facility following the successful completion of the acceptance tests and the Battery Buyoff Review including the satisfactory closeout of all open items.

#### **EQUIREMENT COMPLIANCE VERIFICATION** 2.16

Compliance with all requirements of this document shall be verified. Methods of verification are: verification by analysis, verification by inspection, verification by test, and verification by The manufacturer shall provide a verification matrix defining the method of verification for each specific requirement of this document.

#### UNIT CHARACTERIZATION 2.17

Engineering Development Unit: Designated as (E) and represents a non-flight functional and performance version of the final flight unit.

Qualification Unit: Designated as (Q) and represents a full flight unit that is tested to protoflight levels.

Acceptance Unit: Designated as (A) and represents a full flight unit that is tested to acceptance levels.

#### **VERIFICATION LEVEL** 2.18

Inspection: Designated as (I) and represents inspection of the physical hardware by a customer appointed qualified inspector for compliance.

Analysis: Designated as (A) and represents documentation of performance or function through detailed analysis using all applicable tools and techniques.

Demonstration: Designated as (D) and represents a demonstration of performance and/or functionality through a properly configured demonstration setup where all critical data of the demonstration is captured for review using standard inputs and outputs to the unit.

Test: Designated as (T) and represents a detailed test of performance and/or functionality throughout a properly configured test setup where all critical data taken during the test period is captured for review.

Doc #: ST5-495-006

#### 2.19 VERIFICATION MATRIX

The following matrix identifies each of the functional and performance requirements specified within this documented and identifies how the requirement will be satisfied (i.e., the Level) and in what assembly the requirement will be specified (i.e., the Unit). The entire matrix shall be completed and negotiated with the supplier during Phase B and agreed to prior to the start of Phase C/D/E.

	_	LEVEL UNIT			Γ			
PARAGRAPH#	REQUIREMENT TITLE	I	A	D	T	E	Q	A
							<u> </u>	<u> </u>

## APPENDIX A: SIGNATURE CURVE ANALYSIS OF THE LITHIUM ION CELLS

This test is not required under this contract, but it is included in case the Contractor chooses to perform the test.

A signature curve is a simple method of evaluating the rate performance of Lithium Ion cells. Originally developed by Jean-Marie Tarascon of Bellcore, it determines the rate performance at fractional C rates, typically from C/1 down to C/16, within the expanse of one discharge cycle. It is a fast and reliable method useful for evaluating cells based on rate performance and capacity.

A signature curve test starts with cells that are completely charged. This is important as it sets a common starting baseline. A summary of the method is shown below:

- (a) Start with a fully charged cell.
  - (j) Discharge at C/1 rate to 3.0 V.
  - (k) Rest for 15 minutes at open circuit.
  - (1) Discharge at C/1.5 rate to 3.0 V.
  - (m) Rest for 15 minutes at open circuit.
  - (n) Discharge at C/2 rate to 3.0 V.
  - (o) Rest for 15 minutes at open circuit.
  - (p) Discharge at C/4 rate to 3.0 V.
  - (q) Rest for 15 minutes at open circuit.
  - (r) Discharge at C/8 rate to 3.0~V.
  - (s) Rest for 15 minutes at open circuit.
  - (t) Discharge at C/16 rate to  $3.0\ V.$
  - (u) End

The first discharge to 3.0 V at the C rate is simply the amount of capacity the cell delivers at the C rate. Because of concentration polarization in the electrodes, the cell voltage quickly recovers to about 3.6 volts and then stabilizes. Then the cell is discharged at the C/1.5 rate until the cell voltage again reaches 3.0 V, which it will do in a short time. The mA-hrs delivered at the C/1.5 rate plus the mA-hrs delivered at the C rate is the equivalent of discharging the cell at the C/1.5 rate. The voltage will recover again, but not as high as before. This is repeated for discharge at each rate, with a fifteen-minute open circuit rest between discharges. Since each rate is smaller than the previous, the total amount of mA-hrs discharged for all discharges is the equivalent of discharging the cell at the last rate only.